

Dimensional Stability Test Certificate

Wednesday October 11th, 2017

Supplier: Terra Mater Hardwood Floors Pty Ltd (23-27 Rodeo Drive, Dandenong, VIC 3175)

Sample Description: 5 mm DURAPLANK Vinyl Plank

Date Tested: September 2017 (Tested by FORAY Laboratories – NATA Accreditation 1231)

Test Method: ISO 2551-1990 “Machine-made textile floor coverings – Determination of dimensional changes due to the effects of varied water and heat conditions”.

Test Data:

Mean Linear change when exposed to:	5 mm DURAPLANK Vinyl Plank	Australian Carpet Classification Scheme requirements
Heat at 60°C for 2 hours	Length: 0.00% Width: 0.00%	Length: ±0.2% Width: ±0.2%
Water at 20°C for 2 hours	Length: -0.05% Width: -0.05%	Length: ±0.2% Width: ±0.2%
Heat at 60°C for 24 hours	Length: -0.05% Width: 0.00%	Length: ±0.2% Width: ±0.2%
Standard atmosphere for 48 hours	Length: -0.05% Width: -0.05%	Length: ±0.2% Width: ±0.2%
Degree of cockling observed	None	None
Change in appearance	None	None



Dr. Vyt Garnys
PhD, BSc(Hons) AIMM, ARACI, ISIAQ
ACA, AIRAH, FMA
Managing Director and Principal Consultant



Tuan Duong
BEng(Chemical Engineer)
Consultant



Nick Joy
BSc (Hons)
Consultant

CV170911